


Abbeon Cal, Inc.
1363 Donlon Street Unit 1
Ventura, CA 93003-8387
www.abbeon.com. E-mail: abbeoncal@abbeon.com

EMX Stripheaters for Acrylic Sheet Bending

This heavy duty stripheater is designed to place a narrow strip of heat on an acrylic plastic sheet until it is soft and pliable enough to bend to the desired form. It is capable of heating sheets up to ½" thick.



- Thermostat controlled Low/High (0-10) setting
- ON/Off switch
- Power Indicator Light
- Cord Winding Bracket
- Very sturdy sheet metal construction and baked enamel paint



MODEL EMX2
Max Temp 450°F, Weight 19 lbs

Watts 625, Volts 115AC
Length 48", Width 7"
Replacement Elements: Cat.# EM804817

HOW TO USE THE EMX STRIPHEATER

HEAT FORMING

Acrylic is a thermoplastic material. When heated to approximately 340° f (171° c), it becomes soft and pliable. At this stage it can be formed into almost any shape as it cools. Because acrylic is a thermoplastic, it can be re-heated and will return to its original shape.

STRIPHEATING

The EMX stripheater was designed to place a strip of heat on your acrylic sheet approximately 1" (2.5 cm) wide. The EMX-2 will accept a sheet of acrylic up to 48" (121 cm). It will bend sheets of acrylic from 1/16" (1.6 mm) to 1/2" (12 mm).

OPERATING INSTRUCTIONS

- 1) Turn unit on and see if pilot light is lit. Set rheostat underneath the unit to HI. (Turn clockwise by hand. There is no knob for the rheostat)
- 2) Remove paper masking from acrylic sheet on the part that is exposed to the heat (both front and back).
- 3) Place acrylic sheet over heater and wait for slight rippling changes to occur on the surface. At this point the sheet should be soft enough to bend. Rippling will only occur on thicknesses up to 1/4". Heating times may vary from 1 minute to 30 minutes depending on the thickness of the material.
- 4) Have on hand a jig or some kind of backing against which the bent sheet can be supported without movement while it cools to desired bend.
- 5) To make very sharp bends, cut a "V" groove 90 degrees with a plastic cutting saw on the inside bend area and heat the opposite side of grooved area. The folding radii is determined by the shape of the groove and it's depth.
- 6) AVOID OVER HEATING AS IT WILL CAUSE THE SURFACE TO BURN AND BLISTER. Always experiment with scrap acrylic first.
- 7) To test whether the sheet has been sufficiently heated hold one end of the sheet and flex the other end while the material is still being heated. When it flexes easily, proceed with bending.
- 8) The surface of the stripheater can get hot around the element. Be cautious.

REPLACEMENT PARTS LIST

48" Calrod Heating Element for model EMX-2 Cat.#EM804817
Toggle Switch..... Cat.#EM804825
Thermostat Control Switch..... Cat.#EM804826
End Cap Support Cat.#EM804827

WARRANTY

Your unit is guaranteed against defective workmanship and material. This guarantee does not include repair or replacement due to misuse, abuse, or normal wear and tear. This guarantee ends one year after date of purchase.



Abbeon Cal, Inc.

1363 Donlon Street Unit 1

Ventura, CA 93003-8387

www.abbeon.com. E-mail: abbeoncal@abbeon.com